

•

•

•

•

•

	ASTM D 1544-04	1.0Gmax
	ASTM D 1652-04	170-180
	ASTM D 3236-09	1100-1700cP
	ASTM D 1726-03	0.1%max
	ASTM D 1652-04	5.56-5.81



	ASTM D 1475-98	1.18g/ml
	ASTM E 203-01	0.1%max
	TEC-AS-P-023	10ppm max
	ASTM D 93	> 150°C

4.